

BLANCO ALBA



CUARCITA
DE VENEIRA



BLANCO ALBA

TECHNICAL SPECIFICATIONS

Petrographic denomination	Two mica granite	UNE-EN 12407
Apparent density	2640 Kg/m ³	UNE-EN 1936
Water absorption	0.3 %	UNE-EN 13755
Abrasion resistance	15.1 mm.	UNE-EN 14157
Breaking load at dowel hole	2050 N.	UNE-EN 13364
Compressive strenght	188 MPa	UNE-EN 1926
Flexural strenght	15.3 MPa	UNE-EN 12372
Frost resistance (Decrease of Rf after 48 cycles)	4.6 %	UNE-EN 12371
Slip resistance	Polished: 83/12 SRV Honed: 68/19 SRV	UNE-EN 14231

Cuarcitas Aveneira S.L.

Veneira de Roques
27336 A Pobra do Brollon (Lugo - España)
Teléfono: + 34 982 530 053
Fax: + 34 982 530 347
E-mail: info@cuarcitadeveneira.com

Delegación en Argelia

Rue Mouloud Zadi, 7 - 1 Et.
Sacre Coeur - Alger
Tfnos.
00213 554965992
00213 552330117