



CREMA TERRA



CUARCITA
DE VENEIRA



CREMA TERRA

TECHNICAL SPECIFICATIONS

Petrographic denomination	Boitite granite	UNE-EN 12407
Apparent density	2610 Kg/m ³	UNE-EN 1936
Open porosity	1.0 %	UNE-EN 1936
Water absorption	0.3 %	UNE-EN 13755
Abrasion resistance	15.2 mm.	UNE-EN 14157
Breaking load at dowel hole	2000 N.	UNE-EN 13364
Compressive strenght	157 MPa	UNE-EN 1926
Flexural strenght	11.6 MPa	UNE-EN 12372
Frost resistance (Decrease of Rf after 48 cycles)	2.5 %	UNE-EN 12371
Slip resistance	Polished: 59/7 SRV Honed: 62/16 SRV	UNE-EN 14231

Cuarcitas Aveneira S.L.

Veneira de Roques
27336 A Pobra do Brollon (Lugo - España)
Teléfono: + 34 982 530 053
Fax: + 34 982 530 347
E-mail: info@cuarcitadeveneira.com

Delegación en Argelia

Rue Mouloud Zadi, 7 - 1 Et.
Sacre Coeur - Alger
Tfnos.
00213 554965992
00213 552330117