

GRAN PERLA



CUARCITA
DE VENEIRA



GRAN PERLA

TECHNICAL SPECIFICATIONS

Petrographic denomination	Biotite granite	UNE-EN 12407
Apparent density	2650 Kg/m ³	UNE-EN 1936
Open porosity	0.9 %	UNE-EN 1936
Water absorption	0.3 %	UNE-EN 13755
Abrasion resistance	15.6 mm.	UNE-EN 14157
Breaking load at dowel hole	3250 N.	UNE-EN 13364
Compressive strenght	149 MPa	UNE-EN 1926
Flexural strenght	12.7 MPa	UNE-EN 12372
Frost resistance (Decrease of Rf after 48 cycles)	10.3 %	UNE-EN 12371
Slip resistance	Polished: 66/6 SRV Honed: 61/28 SRV	UNE-EN 14231

Cuarcitas Aveneira S.L.

Veneira de Roques
27336 A Pobra do Brollon (Lugo - España)
Teléfono: + 34 982 530 053
Fax: + 34 982 530 347
E-mail: info@cuarcitadeveneira.com

Delegación en Argelia

Rue Mouloud Zadi, 7 - 1 Et.
Sacre Coeur - Alger
Tfnos.
00213 554965992
00213 552330117